

Code	Kleur	Bruto Densiteit	Netto Densiteit	Hardheid 40%	Maximale uitrekking	Treksterkte	Veerkracht	Compressieset 50%, 22h, 70 °C	Wet Compression Set 95%, 22h, 40 °C	Brandnorm BS 5852
		(kg/m ³)	DIN EN ISO 845 (kg/m ³)	DIN EN ISO 3386 DEEL 1 (kPa)	DIN EN ISO 1798 (%)	DIN EN ISO 1798 (kPa)	DIN EN ISO 8307 (%)	DIN EN ISO 1856 (%)	NFT 56 112 (%)	CRIB 5
CME 20 S	LICHT BEIGE	20	18	1,7	> 65	> 60	> 37	< 25	< 50	✓
CME 28 M	BEIGE/ANTR.	28	26	3,6	> 85	> 95	> 40	< 7	< 30	✓
CME 35 H	ORANJE	35	33	4,0	> 90	> 90	> 47	< 6	< 8	✓
CME 40 M	WIT	40	38	4,0	> 115	> 95	> 48	< 5	< 7	✓
CME 40 H	LICHT GEEL	40	38	5,0	> 90	> 105	> 45	< 6	< 6	✓